

## TEST REPORT

Hardline Laboratory

Report No. : HLB0088/2025

Page : 1 of 2

Date : NOV. 17, 2025

### **SUPER SHENG ENTERPRISE CO., LTD.**

NO. 6, LANE 151, MINSHENG ST., SANHSIA DIST, NEW TAIPEI CITY, TAIWAN 23741

### **The following merchandise was submitted and identified by the applicant as:**

Product Description: SUPERSEN STAINLESS BRACKET (BALL SUS303 / PLATE SUS304)

Style/Item No.: BKTS-34

Manufacturer/Vendor: SUPER SHENG ENTERPRISE CO., LTD

Country of Origin: TAIWAN

### **We have tested the submitted sample(s) as requested and the following results were obtained:**

Test Requested: Pulling Test

Test Method:


1. Secure the sample on the testing machine. (As shown in Photo B)
2. Apply an increasing upward force to the sample until it is broken or damaged.
3. Record the max. force and any findings.
4. Testing Machine: INSTRON 5982; Rate: 10 mm/min.
5. Diameter of steel cable Ø 3.0 mm

Test Result: --- See following sheets ---

Date of Receipt: Nov. 07, 2025

Testing Period: Nov. 07, 2025 ~ Nov. 17, 2025

Signed for and on behalf of  
SGS Taiwan Ltd.

  
Sturm Su  
Manager



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

## TEST REPORT

Hardline Laboratory

Report No. : HLB0088/2025




Page : 2 of 2

### Test Result:

Sample	Max. force (kgf)	Finding
SUPERSEN STAINLESS BRACKET (BALL SUS303 / PLATE SUS304)	413	The sample was broken after testing.

**Note:** The content of this report is invalid if it is not presented as the entire report.

### – Picture(s) –

	
<p>Photo A: Appearance of the sample</p>	<p>Photo B: Test setup</p>
	<p>--Blank--</p>
<p>Photo C: After testing</p>	<p>--Blank--</p>

---End of Report---

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.